



W H COLLIER

Handmade Bricks Since 1863

BRICK TYPE		HANDMADE			
DESCRIPTION/ APPEARANCE		TRADITIONAL HAND MOULDED BRICKS, FROGGED AND LIGHTLY CREASED ON BOTH HEADER AND STRETCHER FACES. MADE TO BS EN771-1. (SOLID BRICKS AVAILABLE TO ORDER)			
WORK SIZES (MM)		METRIC	215 x 102.5 x 65		NON-STANDARD, BRIQUETTE & LINEAR SIZES ALSO AVAILABLE
		IMPERIAL	228 x 110 x 68		
		TUDOR (2")	215 x 102.5 x 50		
SPECIALS		BRITISH STANDARD AND BESPOKE SPECIALS AVAILABLE. MADE TO BS 4729 & BS EN771-1			
BRICK RANGE		ANGLIAN		PRIMROSE	
DIMENSIONAL TOLERANCE	TOLERANCE CLASS	T2		T2	
	RANGE CLASS	R1		R1	
COMPRESSIVE STRENGTH		28.7 N/MM ²		40 N/MM ²	
WATER ABSORPTION		17%		18%	
SOLUBLE SALTS		S2		S2	
DURABILITY (FREEZE THAW)		F2		F2	
REACTION TO FIRE		CLASS A1		CLASS A1	
PACKAGING		STRAP BANDED WITH 2 FORK VOIDS. ALL PACKS ARE INTERLEAFED WITH STRAW			
PACK SIZES & WEIGHTS		SIZE (MM)	QTY/	WT. (KG)	DRY WT. /BRICK (KG)
		50	515	850	1.6
		65	400	850	2.5
		68	320	850	2.8
WORKMANSHIP		<p>TO ACHIEVE A UNIFORM COLOUR BLEND THROUGHOUT, ALWAYS MIX WHERE POSSIBLE FROM MULTIPLE PACKS, BUT AT LEAST 3.</p> <p>REMOVING BRICKS VERTICALLY NOT HORIZONTALLY THROUGH THE PACKS.</p> <p>OUR HANDMADE BRICKS SHOULD BE LAID 'FROG UP', ENSURING A CONSISTENT APPEARANCE.</p> <p>ENSURE BRICKS & BRICKWORK IS COVERED AT ALL TIMES DURING BUILDING, PREVENTING SATURATION FROM RAIN, FROST, SNOW OR SPLASHING.</p>			
SAMPLES		<p>IT IS ADVISED THAT BRICK SAMPLES ARE VIEWED BEFORE PLACING AN ORDER AS ACTUAL COLOURS MAY VARY FROM THOSE VIEWED ON-LINE DUE TO SCREEN AND PRINT LIMITATIONS.</p> <p>SAMPLES, AVAILABLE IN 3 BRICK BOXES OR SAMPLE PANELS CAN BE ORDERED THROUGH OUR SALES OFFICE AND ARE USUALLY AVAILABLE WITHIN 24 HOURS.</p> <p>60 BRICK SITE PANELS AVAILABLE ON REQUEST.</p>			

